



A brand of ITW Polymers Adhesives North America

Technical Data Sheet

1/26/2012

Ceramic Repair Compound

Description:	A high performance, trowelable, ceramic-filled epoxy for rebuilding worn or damaged equipment.
Intended Use:	Rebuild worn pump casings and suction plates; repair tube sheets, heat exchangers and other circulating water equipment; restore worn chutes and hoppers; repair and rebuild butterfly and gate valves.
Product features:	Excellent chemical resistance Resists corrosion, erosion and cavitation Non-sagging, creamy putty
Limitations:	None

Typical Physical Properties:

Technical data should be considered representative or typical only and should not be used for specification purposes.

Cured 7 days @ 75° F

Adhesive Tensile Shear	2,231 psi
Coefficient of Thermal Expansion	20 [(in)(in)x°F]x10(-6)
Color	Dark Blue
Compressive Strength	10,240 psi
Coverage/lb	72 sq.in./lb. @ 1/4"
Cured Hardness	86D
Cured Shrinkage	0.0024 in./in.
Dielectric Constant	38
Dielectric Strength	350 volts/mil
Flexural Strength	5,870 psi
Functional Cure	16 hrs.
Mix Ratio by Volume	3.3 : 1
Mix Ratio by Weight	4.7 : 1
Mixed Viscosity	Putty
Modulus of Elasticity	8.1 x 10(5) psi
Pot Life @ 75F	45 minutes
Recoat Time	3-5 hours
Solids by Volume	100 %
Specific Gravity	1.55
Specific Volume	17.9 in.(3)/lb.
Temperature Resistance	Wet 150 °F; Dry 350 °F
Thermal Conductivity	1.72 [(cal)/(sec xcm x°C)x10-

TESTS CONDUCTED

Adhesive Tensile Shear ASTM D 1002
 Coef. of Thermal Expansion ASTM D 696
 Compressive Strength ASTM D 695
 Cured Hardness Shore D ASTM D 2240
 Cure Shrinkage ASTM D 2566
 Dielectric Constant ASTM D 150
 Dielectric Strength, volts/mil ASTM D 149
 Flexural Strength ASTM D 790
 Modulus of Elasticity ASTM D 638
 Thermal Conductivity ASTM C 177

Surface Preparation:

1. Thoroughly clean the surface with Devcon® Cleaner Blend 300 to remove all oil, grease and dirt.

2. Grit blast surface area with 8-40 mesh grit, or grind with a coarse wheel or abrasive disc pad, to create increased surface area for better adhesion (Caution: An abrasive disc pad can only be used provided white metal is revealed). Desired profile is 3-5mil, including defined edges (do not "feather-edge" epoxy).

Note: For metals exposed to sea water or other salt solution, grit-blast and high-pressure-water-blast the area, then leave overnight to allow any salts in the metal to "sweat" to the surface. Repeat blasting to "sweat out" all soluble salts. Perform chloride contamination test to determine soluble salt content (should be no more than 40ppm).

3. Clean surface again with Devcon® Cleaner Blend 300 to remove all traces of oil, grease, dust or other foreign substances from the grit blasting.

4. Repair surface as soon as possible to eliminate any changes or surface contaminants.

WORKING CONDITIONS: Ideal application temperature is 55°F to 90°F. In cold working conditions, directly heat repair area to 100-110°F prior to applying epoxy and maintain at this temperature during product cure to dry off any moisture, contamination or solvents, as well as to achieve maximum performance properties.

Mixing Instructions:

---- It is strongly recommended that full units be mixed, as ratios are pre-measured. ----

1. Add hardener to resin.
2. Mix thoroughly with screwdriver or similar tool (continuously scrape material away from sides and bottom of container) until a uniform, streak-free consistency is obtained.

INTERMEDIATE SIZES (1,2,3 lb. units): Place resin and hardener on a flat, disposable surface such as cardboard, plywood or plastic sheet. Use a trowel or wide-blade tool to mix the material as in Step 2 above.

LARGE SIZES: (25 lb., 30 lb., 50 lb. buckets): Use a T-shaped mixing paddle or a propeller-type Jiffy Mixer Model ES on an electric drill. Thoroughly fold putty by vigorously moving paddle/propeller up and down until a homogenous mix of resin and hardener is attained.

Application Instructions:

Spread mixed material on repair area and work firmly into substrate to ensure maximum surface contact. Ceramic Repair Compound fully cures in 16 hours, at which time it can be machined, drilled, or painted.

FOR BRIDGING LARGE GAPS OR HOLES

Place fiberglass sheet, expanded metal, or mechanical fasteners between repair area and Ceramic Repair Compound prior to application.

FOR VERTICAL SURFACE APPLICATIONS

Ceramic Repair Compound can be troweled up to 1/2" thick without sagging. Chemical immersion is possible after 24 hours.

FOR MAXIMUM PHYSICAL PROPERTIES

Cure at room temperature for 2.5 hours, then heat cure for 4 hours @ 200 °F.

FOR ± 70 °F APPLICATIONS

Applying epoxy at temperatures below 70 °F lengthens functional cure and pot life times. Conversely, applying above 70 °F shortens functional cure and pot life.

Storage:

Store at room temperature, 70 °F.

Compliances:

ABS (American Bureau of Shipping)

Chemical Resistance:

Chemical resistance is calculated with a 7 day, room temp. cure (30 days immersion) @ 75 °F

1,1,1-Trichloroethane	Excellent	Nitric 50%	Poor
Aluminum Sulfate 10%	Excellent	Phosphoric 10%	Very good
Benzene	Excellent	Potassium Hydroxide 40%	Excellent
Chlorinated Solvent	Excellent	Sodium Hydroxide 10%	Excellent
Gasoline (Unleaded)	Excellent	Sodium Hydroxide 50%	Excellent
Hydrochloric 10%	Excellent	Sulfuric 10%	Excellent
Kerosene	Excellent	Sulfuric 50%	Very good
Mineral Spirits	Excellent		

Precautions:

Please refer to the appropriate material safety data sheet (MSDS) prior to using this product.

For technical assistance, please call 1-800-933-8266

FOR INDUSTRIAL USE ONLY

Warranty:

Devcon will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

Disclaimer:

All information on this data sheet is based on laboratory testing and is not intended for design purposes. ITW Devcon makes no representations or warranties of any kind concerning this data.

Order Information:

11730 32 lb.