



Technical Data Sheet

QLE 1100

43 Shore A, Clear, Addition Cure, One Part Elastomer for Coating Applications

PRODUCT DESCRIPTION

QLE 1100 is a 100% silicone solids elastomer designed for use as a conformal coating, but can also be used for cloth coating applications.

KEY FEATURES

- 100% solids
- Transparent, ideal for pigmentation
- Fast cure at elevated temperatures
- Good abrasion resistance
- Primerless adhesion to many substrates
- Low viscosity

TYPICAL PROPERTIES

UNCATALYZED	
PROPERTY	QLE 1100
Appearance	Clear to light brown
Viscosity	1,000 cps
Specific Gravity	1.01

CURED PROPERTIES*	
30 minutes @ 150°C	
PROPERTY	RESULT
Durometer, Shore A	43
Tensile	90 psi
Elongation	50 %
Useful temperature range	- 55C – 204C

* For physical property testing, these materials have been cured in a closed mold at extended times to ensure full cure. When cured in an open environment, the cure time will be faster than in a closed mold, at the same temperatures. It is recommended that the material cure profile be optimized for the environment it will ultimately be used in.

CURE PROFILE	
TEMPERATURE	TIME
200°C	5 minutes
150°C	30 minutes



Technical Data Sheet

USE and APPLICATION

This material is a one-component, translucent, heat-cured silicone elastomer. The material should only be used on clean surfaces to maximize adhesion properties. In addition, some substrates may be difficult to bond to and some, such as galvanized metal, may cause cure inhibition. When this occurs, a primer can be used to eliminate this problem.

STORAGE AND SHELF LIFE

If QLE 1100 is stored in an environment that does not exceed 40°F then QSi will warranty the material for a period of 6 months from the date of shipment.

DISCLAIMER

The technical data listed is provided for reference only and is not intended as product specifications. QSi has the capability to customize products as requested. For sales and technical assistance please contact customer service at (804) 271-9010 or 1-800-852-3147.

*Please be sure to visit our website daily for our complete product portfolio,
new product introductions and more! www.quantumsilicones.com*

Quantum Silicones Headquarters
7820 Whitepine Road
Richmond, VA 23237

Manufacturing, Research and Development Facility
8021 Reycan Road
Richmond, VA 23237

Phone: 804-271-9010
Fax: 804-271-9055
Toll Free: 800-852-3147