



## Permatex® Zip Grip® GPE 30

<b>Description:</b>	A single component low viscosity, general purpose cyanoacrylate adhesives for tight fitting parts
<b>Intended Use:</b>	Ideal for bonding pre-assembled parts, rubber and leather. Product designed to set and adhere rapidly to inactive surfaces
<b>Product features:</b>	<b>Easy to apply</b> <b>Fixtures in seconds</b> <b>Permanent</b> <b>Bonds to inactive surfaces</b> <b>All purpose [low viscosity]</b>
<b>Limitations:</b>	

**Typical Physical Properties:**

*Technical data should be considered representative or typical only and should not be used for specification purposes.*

**Cured 7 days @ 75° F**

<b>Adhesive Tensile Shear</b>	<b>3,200 psi [steel/steel]</b>
<b>Coefficient of Thermal Expansion</b>	<b>.000126 in./in./°F</b>
<b>Dielectric Constant</b>	<b>5.4 @ 1 Kc</b>
<b>Dielectric Strength</b>	<b>11.6 KV/mm</b>
<b>Flashpoint</b>	<b>185°F</b>
<b>Full Cure</b>	<b>24 hours</b>
<b>Melting Point</b>	<b>329°F</b>
<b>Refractive Index</b>	<b>1.49</b>
<b>Service Temperature Range</b>	<b>-65°F to 200°F</b>
<b>Shelf Life</b>	<b>1 year</b>
<b>Solubility</b>	<b>Nitromethane, Acetone,</b>
<b>Volume Resistivity</b>	<b>5.3E-14 ohm/cm</b>

**TESTS CONDUCTED**

Adhesive Tensile Shear ASTM D 1002
Coef. of Thermal Expansion ASTM D 696
Dielectric Constant ASTM D 150
Volume Resistivity , ohm/cm ASTM D 149
Dielectric Strength, volts/mil ASTM D 149

**Uncured**

<b>Base</b>	<b>Ethyl cyanoacrylate</b>
<b>Color</b>	<b>Colorless liquid</b>
<b>Cure Speed</b>	<b>5-12 sec. (Steel); 5-13 sec. (Plastics): &lt;6 sec</b>
<b>Gap Filling</b>	<b>0.004"</b>
<b>Military Specification</b>	<b>Mil-A-46050C Type II, Class 1</b>
<b>Specific Gravity</b>	<b>1.06 g/cc</b>
<b>Viscosity</b>	<b>30 cps</b>

**Surface Preparation:**

Clean surface by solvent-wiping any deposits of heavy grease, oil, dirt, or other contaminants. Surface can also be cleaned with industrial cleaning equipment such as vapor phase degreasers or hot aqueous baths.

---- CLEANING METHODS ----

**STEEL:**

Vapor degrease or cold-solvent clean (Sand blasting or other preparation is not typically required).

**ALUMINUM:**

Abrade with Scotch-Brite™ abrasive pads or steel wool, then clean with solvent.

**RUBBER:**

Wipe clean with isopropyl alcohol or solvent.

**PLASTICS:**

Lightly abrade shiny, smooth surfaces, then solvent-wipe with suitable solvent such as 1,1,1-trichloroethane, acetone, or VM&P naphtha. Non-shiny surfaces need only be solvent-wiped.

**Mixing  
Instructions:**

Mixing is not applicable to this product.

**Application  
Instructions:**

1. Apply adhesive directly from bottle [approx .006 gms per sq. in is sufficient]
2. Press surfaces together
3. Hold tightly for a few seconds

**ADDITIONAL PRODUCT INFORMATION**

- Cyanoacrylates fixture in a few seconds on most smooth, close fitting substrates
- They cure best at room temperature [72°F]
- Heat does NOT accelerate the cure of cyanoacrylates
- The gap of the bond line will affect set speed. Smaller gaps tend to increase the speed.
- Activators can be applied to improve set speed but may also impair overall performance.

**Storage:**

Store in a cool, dry place.

**Compliances:**

CID A-A-3097, Type II, Class 1

**Chemical  
Resistance:**

*Chemical resistance is calculated with a 7 day, room temp. cure (30 days immersion) @ 75°F*

1,1,1-Trichloroethane	Excellent
Gasoline (Unleaded)	Excellent
Hydrochloric 10%	Poor
Motor Oil	Excellent
Perchloroethylene	Excellent
Sodium Hydroxide 10%	Poor

**Precautions:**

Please refer to the appropriate material safety data sheet (MSDS) prior to using this product.

**For technical assistance, please call 1-800-933-8266**

**FOR INDUSTRIAL USE ONLY**

**Warranty:**

Devcon will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

**Disclaimer:**

All information on this data sheet is based on laboratory testing and is not intended for design purposes. ITW Devcon makes no representations or warranties of any kind concerning this data.

**Order  
Information:**

**70350 1 oz.**  
**70361 1 lb.**