



9411 Corsair Road Frankfort, IL 60423 1-800-552-0299 Phone 1-815-464-5650 Fax

EMERGENCY PHONE 1-800-255-3924

TECHNICAL DATA SHEETS MP 54110

Description:

MP 54110 is a two part unfilled epoxy adhesive designed for bonding of metals, ceramics and most plastics. This product gives good resistance to water, salt spray, inorganic acids and bases and most organic solvents. This product gives better water and temperature resistance than standard 5 minute epoxy.

It was especially formulated to a 1:1 mix ratio for use in either MMD equipment or side by side dual cartridges for easy dispensing. A handling cure is normally achieved at room temperature within 30 - 60 minutes with full cure in 24 hours. An elevated temperature cure schedule can be used to reach final properties quickly.

Instructions:

- 1) Bring both components to room temperature prior to mixing. Mix 1 parts A to 1 part B thoroughly.
- 2) Allow to cure undisturbed until product is fully gelled or tackfree to the touch.
- 3) Clean up uncured resin with suitable organic solvent such as MEK, acetone or a chlorinated.solvent.

Mix Ratio:

1A:1B by weight or 1A:1B by volume.

Many epoxy resin systems are prone to crystallization as epoxy resin is a super-cooled fluid. This condition may give the product a gritty or grainy appearance (or hazy in clear products). In extreme cases it may appear solid and cured. Fluctuating temperatures (within 0 to 50° C) aggravate this phenomena. Heating to 50 to 60° C with stirring can usually restore products. Storage at 25 +/- 5° C is optimum for most products.

Handling and Physical Properties:

All properties given are at 25°C unless otherwise noted.

Color Viscosity	Part A Part B Mixed	Clear 12,000 cps 20,000 cps 15,000 cps (est)
Specific Gravity Pot Life Mass	/ Part A Part B Mixed	1.17 1.15 1.16 8 - 12 minutes 20 grams
Tensile Strength Lap Shear (Al to Al) T-Peel		2300 psi 3 – 5 pli *
Temperature Range		-40 to 130°C
Hardness		80

Linear Coefficient of Thermal Expansion (x 10 (6))/ °C 62 *

Shore -D

Shelf Life:

12 Months

Method

Engineering Excellence

For technical information and support call 1-800-552-0299 or visit our website at

