

**EMERGENCY PHONE 1-800-255-3924**  
**TECHNICAL DATA SHEETS**  
**MG 500**

**Description:**

**MG500** is a medical grade instant adhesive. These products have USP Class VI certification and are used in assembling medical devices.

**Physical Properties:**

COLOR: Clear  
 VISCOSITY: 500 cps  
 BASE: Modified Ethyl  
 STRENGTH: 2700/4300  
 TEMPERATURE RANGE: - 65 - 200°F  
 CURE SPEED: 15 seconds  
 (FIXTURE)  
 FULL CURE: 8 hours  
 MIL A 46050 Type II  
 Class II  
 SPECIFIC GRAVITY 1.05  
 SOLUBLE IN: Remove Debonder

**Storage**

The MG series is ideally stored in a cold, dry location in unopened containers. Optimal storage temperature is under 50°F. To prevent contamination of unused product, do not return any material to its original container.

**Handling Characteristics:**

Shear Strength, ASTM D1002, DIN 53283	Value	Range
Grit Blasted Steel, N/mm <sup>2</sup> (psi)	23 (3250)	20 to 28 (2910 to 3970)
Etched Aluminum, N/mm <sup>2</sup> (psi)	17 (2450)	13 to 22 (1950 to 3125)
ABS, N/mm <sup>2</sup> *	>7 (>885)	
PVC, N/mm <sup>2</sup> *	>7 (>890)	
Polycarbonate, N/mm <sup>2</sup> *	>6 (>825)	
Phenolic, N/mm <sup>2</sup> *	12 (160)	6 to 18 (775 to 2450)
Neoprene rubber, N/mm <sup>2</sup> *	>12 (>1600)	
Nitrile rubber, N/mm <sup>2</sup> *	>12 (>1600)	
Tensile Strength, ASTM D2095, DIN 53283		
Grit Blasted Steel, N/mm <sup>2</sup> (psi)	20 (3000)	14 to 28 (1900 to 4000)

\* Substrate Failure

**Engineering Excellence**

For technical information and support call **1-800-552-0299** or visit our website at

**[www.instantca.com](http://www.instantca.com)**