

Fastweld 10 A/B Epoxy Adhesive

Product Description

Fastweld 10 A/B Epoxy Adhesive is a rapid-setting, two-component paste offering a convenient one- to-one mixing ratio by volume or weight. Fastweld 10 A/B Epoxy Adhesive produces strong bonds in a very short period. It is especially suited for bonding small parts and repair work.

Features

- Rapid setting paste
- 1:1 mixing ratio

Typical Properties*

Property	Test Method	Fastweld 10 A Resin	Fastweld 10 B Hardener	Mixed System
Appearance	Visual	Black	White	Gray
Density at 25°C, g/cm ³	ASTM D792	1.48	1.44	1.46
Viscosity at 23°C, cP	ASTM D2393	260,000	160,000	250,000 [†]

*Properties are based on Huntsman test methods. Copies are available upon request.

[†]Measured at 25°C.

Processing

Mix Ratio

Product	Parts by weight	Parts by volume
Fastweld 10 A Resin	100	1
Fastweld 10 B Hardener	100	1

Mix only that quantity which can be applied immediately after mixing. Due to the very fast setting properties of Fastweld 10, hand mixing of the components should be avoided. Fastweld 10 is available in 50 mL twin cartridges. For best results, Fastweld 10 should be dispensed using manual or pneumatic dispensing equipment through a 0.25 in diameter, 20 element static mixing nozzle (Nordson EFD #7701488 or equivalent). For other mixing and application recommendations, please consult your local Huntsman Advanced Materials representative or one of our distributors.

Processing Data

Parameter	Value
Pot life, 2 fl oz at 25°C, min	3 - 4
Typical cure cycle	4 h at 25°C, curing at elevated temperatures is not recommended

Typical Physical Properties

Unless otherwise stated, the data were determined with typical production batches using standard test methods. They are typical values only, and do not constitute a product specification. The figures below were all determined by testing standard specimens made up by lap-joint 4 in x 1 in x 0.06 in (10 cm x 2.5 cm x 1.5 mm) strips of degreased and 100-grit abraded aluminum. The joint area was 0.5 x 1 in (12.5 mm x 2.5 cm) in each case. Samples were cured for 24 h at 77°F (25°C), unless a different cure is specified.

Property	Value
Tensile lap shear at 25°C, psi (MPa) Cure:	
1 h 41°F (5°C)	1,420 (10)
4 h 41°F (5°C)	1,560 (11)
24 h 41°F (5°C)	1,710 (12)
30 min 77°F (25°C)	1,710 (12)
1 h 77°F (25°C)	2,130 (15)
4 h 77°F (25°C)	2,840 (20)
24 h 77°F (25°C)	2,840 (20)
Tensile lap shear, * psi (MPa) Test temperature:	
-40°F (-40°C)	1,560 (11)
77°F (25°C)	2,840 (20)
104°F (40°C)	2,420 (17)
140°F (60°C)	1,140 (8)
Tensile lap shear, exposure to 120°F (49°C) / 95 % R.H., psi (MPa)	
0 day	2,840 (20)
10 days	1,710 (12)
30 days	1,000 (7)
Tensile lap shear, heat aging at 140°F (60°C), psi (MPa)	
0 day	2,840 (20)
10 days	2,840 (20)
30 days	2,990 (21)
60 days	2,560 (18)

*Load applied 10 minutes after specimens reach test temperature.

Storage

Fastweld 10 A/B Epoxy Adhesive should be stored in a dry place in the original sealed containers, at temperatures between 2°C and 40°C (36°F and 104°F). Under these storage conditions, and when supplied under Huntsman standard certification, the product has a shelf life of **3 years** (from date of manufacture). The product should not be exposed to direct sunlight.

If stored below 60°F, the adhesive should be brought to 60°F - 77°F and conditioned at this temperature for some time prior to use.

Precautionary Statement

Huntsman Advanced Materials Americas LLC maintains up-to-date Safety Data Sheets (SDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material.

First Aid!

Refer to SDS as mentioned above.

KEEP OUT OF REACH OF CHILDREN

FOR PROFESSIONAL AND INDUSTRIAL USE ONLY

Important Legal Notice

Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., or Huntsman Advanced Materials (Hong Kong) Ltd. ("Huntsman"). The following supercedes Buyer's documents.

Huntsman warrants that at the time and place of delivery all Products sold to Buyer shall conform to the specifications provided to Buyer by Huntsman.

While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN (EXCEPT AS SET FORTH ABOVE REGARDING CONFORMANCE WITH SPECIFICATIONS PROVIDED TO BUYER BY HUNTSMAN) IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. The Buyer should obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, and should comply with all applicable governmental laws, regulations and standards relating to the handling, use, storage, distribution and disposal of, and exposure to the Product. Buyer shall also take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product, and the containers or equipment in which the Product may be handled, shipped or stored.

Araldite is a registered trademark of Huntsman LLC or an affiliate thereof in one or more, but not all countries.

© 2015 Huntsman Advanced Materials Inc.

Main Offices:

Huntsman Corporation
10003 Woodloch Forest Dr
The Woodlands, TX 77380
888-564-9318

Huntsman Advanced Technology Center
8600 Gosling Rd.
The Woodlands, TX 77381
281-719-7400