

LORD® 7800 Fast Cure Urethane Adhesive

Description

LORD® 7800 adhesive is an equal-mix, two-component urethane adhesive system used to bond composites, SMC and plastics with little surface preparation. This adhesive will also bond painted metals, such as powder-coated, primed and e-coated. LORD 7800 adhesive system offers a range of working times by shifting between LORD 7800 curatives, accommodating a wide variety of process requirements while retaining the same mechanical and adhesion properties.

Features and Benefits

Rapid Cure Strength – provides rapid, outstanding cure strength development, allowing for faster manufacturing and processing.

Consistent Cure Speeds – low exotherm cure (rate of cure less affected by bondline thickness).

Low Tooling Temperature – allows accelerated cure with low heat up to 220°F (104°C), eliminating quality issues from ‘cold spots’ seen with other adhesives.

Enhanced Regulatory Profile – free of heavy metals.

Environmentally Recommended – does not contain ozone depleting chemicals.

Environmentally Resistant – resists weathering, humidity and salt spray.

Non-Sag – remains in position when applied on vertical or overhead surfaces, allowing for greater process flexibility.

Typical Properties*

	7800A Resin	7800C Curative	7800D Curative	7800E Curative	7800F Curative
Appearance	Black	Tan	Tan	Tan	Tan
	Liquid	Liquid	Liquid	Liquid	Liquid
Viscosity, cP @ 77°F (25°C)	20,000	35,000	35,000	35,000	35,000
Density					
lb/gal	11.3-11.6	10.2-10.7	10.2-10.7	10.2-10.7	10.2-10.7
(kg/m ³)	(1357-1393)	(1224-1285)	(1224-1285)	(1224-1285)	(1224-1285)
Flash Point, °F (°C)	>200 (>93)	>200 (>93)	>200 (>93)	>200 (>93)	>200 (>93)
Closed Cup					

*Data is typical and not to be used for specification purposes.

LORD TECHNICAL DATA

Application

Surface Preparation – Surfaces should be free of grease, dirt and other contaminants. For plastics, clean the surface with a dry rag wipe or a rag dampened with solvent. Composites may require light abrasion to remove mold releases, then wiped clean to remove dust or applied with peel-ply to expose a clean surface. Painted surfaces should be wiped clean with a lint-free cloth prior to adhesive application. Verify adhesion to the surface or consult with LORD Customer Service for assistance.

Mixing – Mix LORD 7800A resin with the appropriate curative at a 1:1 ratio, by volume. Handheld cartridges will automatically dispense the correct volumetric ratio of each component. Once mixed, the adhesive cures rapidly.

Applying – Apply adhesive using handheld cartridges or automatic meter/mix/dispense equipment.

- Handheld Cartridges (pneumatic applicator gun recommended)
 1. Load the cartridge into the applicator gun and remove the end caps.
 2. Level the plungers by expelling a small amount of adhesive to ensure both sides are level.
 3. Attach mixing tip and expel a mixer's length of adhesive.
 4. Apply adhesive to substrate and mate the parts within the working time of the adhesive. Clamp in position until adhesive reaches handling strength.
- Meter/Mix/Dispense Equipment
Contact your LORD representative if assistance is needed using this equipment.

For optimum adhesion, bondline thickness of LORD 7800 adhesive should be 10-40 mil (254-1016 micron).

Curing – LORD 7800 adhesive will cure to full strength in 24 hours or less at 75°F (24°C), depending on the curative used.

Cleanup – Clean equipment and tools prior to the adhesive cure with organic solvents such as acetone or MEK. Do not use alcohol. Once adhesive is cured, heat the adhesive to 300°F (149°C) or above to soften the adhesive. This allows the parts to be separated and the adhesive to be more easily removed. Some success may be achieved with commercial adhesive strippers.

Typical Properties* of Resin Mixed with Curative

	7800 A/C	7800 A/D	7800 A/E	7800 A/F
Mix Ratio by Volume, Resin to Curative	1:1	1:1	1:1	1:1
Solids Content by Weight, %	100	100	100	100
Working Time, min @ 75°F (24°C)	3	5-6	11-12	18-20
Time to Handling Strength, min @ 75°F (24°C)	12	25	45	80

*Data is typical and not to be used for specification purposes.

LORD TECHNICAL DATA

Typical Cured Properties**

Hardness Shore D	60
Tensile Strength at Break, psi (MPa) ASTM D638, modified	3000 (20.7)
Elongation, % ASTM D638, modified	130
Young's Modulus, psi (MPa) ASTM D638, modified	25,000 (172)
Glass Transition Temperature, °F (°C) ASTM E1640-99, by DMA	117 (47)

Bond Performance**

Substrates	E-coated Steel	Carbon Fiber Reinforce Plastic (CFRP)	Sheet Molded Composite (SMC)
Lap Shear @ Room Temperature, psi (MPa) Failure Mode	3380 (23.3) C/CF	1553 (10.7) FT/A	778 (5.4) SB
Lap Shear @ -30°F (-34°C), psi (MPa) Failure Mode	3573 (24.6) C/CF	400 (2.7) FT/A	— —
Lap Shear @ 180°F (82°C), psi (MPa) Failure Mode	1634 (11.3) C/CF	265 (1.8) A	293 (2.0) A
Lap Shear after 14 days @ 150°F (65°C), 85% RH, psi (MPa) Failure Mode	3045 (21.0) C/CF	627 (4.3) A	693 (4.8) FT/SB
Lap Shear after 500 hours Salt Spray Exposure, psi (MPa) Failure Mode	3056 (21.1) C/CF	977 (6.7) A	575 (4.0) FT/SB
Lap Shear after 500 hours Water Immersion @ 150°F (65°C), psi (MPa) Failure Mode	3454 (23.8) C/CF	1705 (11.7) FT/A	765 (5.3) FT

Substrate

E-coated Steel, 0.032" thick
CRFP - 0/90, 3 plies, 0.002" thick
SMC, polyester, 0.13" thick

Surface Treatment

Dry Rag Wipe
Dry Rag Wipe
Dry Rag Wipe

Bonded Parameters

Metal Lap Shears (ASTM D1002)
Composite Lap Shears (ASTM D3167)

Bond Area

1.0"x0.5"
1.0"x1.0"

Film Thickness

0.020
0.020

Cure

24 hr @ RT
24 hr @ RT

Mix Ratio

1:1 by Volume
1:1 by Volume

Failure Mode Definition

Adhesive Failure
Coating Failure
Cohesive Failure
Fiber Tear
Stock Break

Abbreviation

A
CF
C
FT
SB

**Data is typical and not to be used for specification purposes. Cured Properties and Bond Performance data are the same regardless of the LORD 7800 curative used.

LORD TECHNICAL DATA

Shelf Life/Storage

Shelf life of each component is six months when stored in a clean, dry environment at 65-85°F (18-30°C) in original, unopened container.

After opening, protect adhesive from excessive exposure to moisture by installing desiccant cartridges and/or using dry nitrogen as an inert cover.

Cautionary Information

Before using this or any LORD product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

LORD and "Ask Us How" are trademarks of LORD Corporation or one of its subsidiaries.

LORD provides valuable expertise in adhesives and coatings, vibration and motion control, and magnetically responsive technologies. Our people work in collaboration with our customers to help them increase the value of their products. Innovative and responsive in an ever-changing marketplace, we are focused on providing solutions for our customers worldwide ... Ask Us How.

LORD Corporation World Headquarters

111 Lord Drive
Cary, NC 27511-7923
USA

Customer Support Center (in United States & Canada)

+1 877 ASK LORD (275 5673)

www.lord.com

For a listing of our worldwide locations, visit LORD.com.

©2018 LORD Corporation OD DS4368 (Rev.0 2/18)

