

# Sikagard® 550W Elastocolor

<b>Description</b>	Sikagard® 550W Elastocolor is an elastomeric, crack-bridging, anti-carbonation, acrylic protective coating. Sikagard® 550W Elastocolor provides protection to reinforced concrete from the ingress of carbon dioxide and other aggressive gasses. It offers high resistance to chlorides and other waterborne salts and excellent UV light resistance. Sikagard® 550W Elastocolor will not act as a vapor barrier and will enhance the appearance of the structure.
<b>Where to Use</b>	Protective, crack-bridging coating for concrete, mortar, stucco, masonry, and exterior finishing systems subject to cracking/dynamic movement. For use on building and civil engineering structures subject to cracking or as the top coat in complete repair and protection systems.
<b>Advantages</b>	<ul style="list-style-type: none"> <li>■ Can bridge dynamically moving cracks.</li> <li>■ Excellent carbonation barrier.</li> <li>■ Vapor permeable.</li> <li>■ Provides resistance to weathering and frost.</li> <li>■ Crack bridging properties maintained at low temperatures.</li> <li>■ Excellent long term UV light resistance.</li> <li>■ Can be applied by brush, roller, or airless spray.</li> <li>■ Good color stability.</li> <li>■ Extremely resistant to dirt pick up and mildew.</li> <li>■ Non-flammable as a system.</li> <li>■ Easily maintained silk finish.</li> </ul>
<b>Coverage</b>	Theoretical yield per coat: 100 ft <sup>2</sup> /gal/coat. Recommended 'wet' film thickness: 16 mils/coat. Recommended 'dry' film thickness: 8 mils/coat. Normal coating system is two coats at a total dry film thickness of 16 mils. Consumption is dependent on porosity of substrate. In addition, allowance must be made for surface profile, unavoidable variation in applied film thickness, loss and waste. Sikagard® Elastic Base Coat can be used as a first coat in a two coat system of Sikagard® 550W Elastocolor.
<b>Packaging</b>	5 gal. Hobbock.

## Typical Data

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

<b>Shelf Life</b>	2 years in original unopened container.		
<b>Storage Conditions</b>	Store dry at 40°-95°F (4°-35°C) Condition material to 60°-75°F (15°-25° C) before using. Protect from freezing. If frozen discard.		
<b>Colors</b>	469 standard colors. Custom color-matching available.		
<b>Pot Life</b>	Indefinite, provided proper care is taken in protecting the system from moisture, freezing, contamination, or evaporation.		
<b>Solids Content</b>	<b>by weight</b>	<b>by volume</b>	
Smooth 550W	62%	55%	
Sikagard® 552W	20%	17%	
<b>Tensile Properties (ASTM D-412 modified after 21 days cure)</b>			
Tensile Strength	200 psi		
Elongation at Break	625% at 73°F (23°C)		
Tensile Strength at 0°F (-18°C)	1100 psi		
Elongation at Break at 0°F (-18°C)	225%		
<b>Waiting Time (between coats) and Curing Rates</b>	<b>45°F (8°C)</b>	<b>68°F (20°C)</b>	<b>85°F (30°C)</b>
Sikagard® 552W Primer+Sikagard® 550W	24 hours	12 hours	6 hours
Sikagard® 550W	12 hours	8 hours	6 hours
Rain resistant (at 75% R.H.)	24 hours	4 hours	2 hours
(Note: Over coating old coatings will increase the waiting times by 100%)			
<b>Water Vapor Diffusion (at 16 mils = 400 microns dry film thickness)</b>			
μ - value H <sub>2</sub> O (diffusion coefficient) = 2,146			
SdH <sub>2</sub> O (equivalent air thickness) = 2.6 ft. (0.8 m)			
<b>Carbon dioxide diffusion (at 16 mils = 400 microns dry film thickness)</b>			
<b>*After 2,000 hours</b>			
μ - value CO <sub>2</sub> (diffusion coefficient) = 214,000			
R (equivalent air thickness) = 299 ft. (91 m)			
Sc (Equivalent concrete thickness) = 9 inches (23 cm)			
*accelerated weathering			
<b>Crack-Bridging (at 16 mils = 400 microns DFT)</b>			
Static (at -4°F/-20°C) 30 mils (0.75 mm)			
Dynamic >1000 cycles (at -4°F/-20°C) 12 mils (0.3 mm)			
<b>Moisture Vapor Permeability (ASTM E-96) 14.5 perms</b>			

**PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.**

Construction



Sika®

<b>Resistance to Wind Driven Rain (TT-C-555B)</b>	No passage of water through the coating	
<b>Flame Spread and Smoke Development (ASTM E-84-94)</b>		
Flame Spread: 5	Smoke Development: 5	Class Rating: A
<b>Weathering (ASTM G-23)</b>	10,000 hours	Excellent, no chalking or cracking

## How to Use

**Surface preparation** All surfaces to be coated must be dry, clean, sound, and frost free with curing compound residues and any other foreign matter removed. An open textured sandpaper like surface is ideal (CSP-3). Where necessary, surfaces should be prepared mechanically by blast cleaning or high speed pressure waterjetting. Allow adequate time for drying. Bug holes, cracks or irregularities of substrate should be filled and leveled with SikaTop®, SikaRepair®, SikaQuick® or acrylic surface fillers as appropriate. Cracks 1/32" or greater should be routed and sealed with a polyurethane sealant before coating.

**Priming:** All porous areas or concrete with excessive porosity should be primed using Sikagard® 552W Primer or SikaLatex® R to allow easy application of Sikagard® 550W Elastocolor.

## Mixing

Stir the coating to ensure uniformity using a slow speed (400-600 rpm) drill and 1/2" jiffy style mixing paddle. To minimize color variation when using multiple units, blend two pails of Sikagard® 550W Elastocolor. Use one pail and maintain the second pail to repeat this procedure (boxing) for the entire application.

## Application

Any areas of glass or other surfaces should be masked. Recommended application temperatures (ambient and substrate) 45°-95°F (7°-35°C). Sikagard® 550W Elastocolor can be applied by brush, roller, or spray over entire area moving in one direction. Allow a minimum of two hours prior to re-coating. At lower temperatures and high humidity, waiting time will be prolonged. At higher temperatures, work carefully to maintain a wet edge. As with all coatings, job site mock-ups should always be completed to confirm acceptability of workmanship, material and aesthetics.

**NOTE:** To achieve a dry film thickness of 16 mils, two coats should be anticipated. For maximum adhesion, (especially on porous substrates) the use of Sikagard® 552W is recommended. Sikagard® 552W primer can be applied by brush or roller. Brushing provides more even and pore free coats and better penetration.

## Limitations

- Not designed for use as a traffic bearing surface.
- Substrates must be dry prior to application.
- Minimum age of concrete prior to application is 14 days, depending on curing and drying conditions (moisture content must be below 5%).
- Minimum age of SikaTop®, SikaRepair®, or SikaQuick® prior to application is three days, depending on curing and drying conditions (moisture content must be below 5%).
- Allow sufficient time for substrate to dry after rain or other inclement conditions.
- Protect from freezing. If frozen, discard.
- Sikagard® 550W Elastocolor should not be applied at relative humidity greater than 90%, or if rain is forecast within the specified rain resistance period.
- Maximum crack width 1/32".
- During application, regular monitoring of the wet film thickness and material consumption is advised to ensure that the correct layer thickness is achieved. When over-coating existing coatings, compatibility and adhesion testing is recommended.
- When over-coating Sikaflex® sealants, a prime coat of Sikagard® 550W Elastocolor Accent Base Coat may be necessary over the sealant to minimize dirt pick up on cured coating.
- Do not store Sikagard® 550W Elastocolor in direct sunlight for prolonged periods.
- Strong winds can cause shrinkage if material is applied at lower temperatures.
- Ensure that the primer is thoroughly dry before over-coating to prevent formation of bubbles and blisters, particularly in warmer weather.
- Not recommended for roofing.

**PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.**

KEEP CONTAINER TIGHTLY CLOSED. KEEP OUT OF REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. FOR PROFESSIONAL USE ONLY.

For further information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety related data. Read the current actual Safety Data Sheet before using the product. In case of emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Safety Data Sheet which are available online at <http://usa.sika.com/> or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Safety Data Sheet prior to product use.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. SALE OF SIKA PRODUCTS ARE SUBJECT SIKA'S TERMS AND CONDITIONS OF SALE AVAILABLE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING 201-933-8800.

Visit our website at [usa.sika.com](http://usa.sika.com)

1-800-933-SIKA NATIONWIDE

**Regional Information and Sales Centers.** For the location of your nearest Sika sales office, contact your regional center.

**Sika Corporation**  
201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: 800-933-7452  
Fax: 201-933-6225

**Sika Canada Inc.**  
601 Delmar Avenue  
Pointe Claire  
Quebec H9R 4A9  
Phone: 514-697-2610  
Fax: 514-694-2792

**Sika Mexicana S.A. de C.V.**  
Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537



Sika and Sikagard, SikaTop and MonoTop are registered trademarks. Printed in Canada.

