



Technical Data Sheet

QLE 1032

27 Shore A, Clear, Addition Cure Elastomer for Coating Applications

PRODUCT DESCRIPTION

QLE 1032 is a 100% silicone solids elastomer designed for fabric or cloth coating applications. This two-component system offers a tough coating with excellent adhesion.

KEY FEATURES

- 100% solids
- Long open time
- Excellent adhesion

TYPICAL PROPERTIES

UNCATALYZED		
PROPERTY	QLE 1032 A	QLE 1032 B
Appearance	White	Clear
Viscosity	150,000 cps	15,000 cps
Specific Gravity	1.16	0.97
Mix Ratio by weight, A:B	10:1	

CATALYZED	
MIX RATIO 10:1 by weight	
Catalyzed viscosity	100,000 cps
Gel time at 25°C *	> 72 hours

* Gel time is defined as the time required for the material to become a solid or a semi-solid.

CURED PROPERTIES**	
20 minutes @ 150°C	
PROPERTY	RESULT
Durometer, Shore A	27
Tensile	180 psi
Elongation	350 %

** For physical property testing, these materials have been cured in a closed mold at extended times to ensure full cure. When cured in an open environment, the cure time will be faster than in a closed mold, at the same temperatures. It is recommended that the material cure profile be optimized for the environment it will ultimately be used in.



Technical Data Sheet

MIXING

In order to achieve optimum performance the same lot number of QLE 1032 A and QLE 1032 B should be used.

Mixing by hand:

Catalyze QLE 1032 A with QLE 1032 B at a 10:1 ratio by weight using a clean plastic or metal container of approximately 3 times the volume of the material and mix by hand. Accurate weighing of all components, on a suitable scale, is essential for optimal product performance when mixing by hand. Mix until the material is uniform with no visible striations.

Mixing and dispensing with automatic equipment:

Use a mixing system that will properly mix the QLE 1032 A and QLE 1032 B at a 10:1 ratio by weight.

DE-AERATION

Air trapped during mixing should be removed by vacuum at 29 inches of mercury. During the process the material will expand and intermittent evacuation may be required.

Machine mixed material does not normally need to be de-aired.

STORAGE AND SHELF LIFE

If QLE 1032 A and QLE 1032 B are stored in their original, unopened containers, in an environment that does not exceed 38°C (100°F) then QSi will warranty the material for a period of 12 months from the date of shipment.



Technical Data Sheet

DISCLAIMER

The technical data listed is provided for reference only and is not intended as product specifications. QSi has the capability to customize products as requested. For sales and technical assistance please contact customer service at **(804) 271-9010** or **1-800-852-3147**.

This material is intended for industrial use only.

*Please be sure to visit our website daily for our complete product portfolio,
new product introductions and more! www.quantumsilicones.com*

Quantum Silicones Headquarters

7820 Whitepine Road

Richmond, VA 23237

Manufacturing, Research and Development Facility

8021 Reycan Road

Richmond, VA 23237

Phone: 804-271-9010

Fax: 804-271-9055

Toll Free: 800-852-3147