



9411 Corsair Road Frankfort, IL 60423 1-800-552-0299 Phone 1-815-464-5650 Fax

**EMERGENCY PHONE 1-800-255-3924** 

# TECHNICAL DATA SHEETS MP 5405 BK

**Description:** 

MP 5405 BLACK is a two part unfilled epoxy adhesive designed for ceramics, and most plastics. It cures to a tough semi-rigid material, and is free flowing in viscosity. It gives good resistance to water, salt spray, inorganic acids and bases, and most organic solvents. It was especially formulated to a 1:1 mix ratio for use in either MMD equipment or side-by-side dual cartridges for easy dispensing.

A handling cure is normally achieved at room temperature within 20 - 30 minutes with full cure in 24 hours. An elevated temperature cure schedule can be used to reach final properties quickly.

## Handling and Storage:

- 1) Bring both components to room temperature prior to mixing. Mix 1 parts A to 1 part B thoroughly.
- 2) Allow to cure undisturbed until product is fully gelled or tack-free to the touch.
- 3) Clean up uncured resin with suitable organic solvent such as MEK, acetone or a chlorinated solvent.

#### Mix Ratio:

1A:1B by weight or 1A:1B by volume.

#### **Shelf Life:**

12 Months

### **Handling Characteristics:**

All properties given are at 25C unless otherwise noted.

Color	Black	
Viscosity	Part A Part B Mixed	14,000 cps 15,000 cps 14,500 cps
Specific Gravity	Part A Part B Mixed	1.16 1.15 1.16
Pot Life Mass	3 - 5 minutes 20 grams	
Tensile Strength Lap Shear (Al to Al)	2300 psi	
Tensile Elongation Tensile Strength Temperature Range	3 - 5% 7000 psi -40 to 130C	
Hardness Method	80 Shore -D	

Linear Coefficient of Thermal Expansion (x 10 (6))/C 62

Dielectric Constant (25C, 100Hz)

4.5

Dielectric Strength 410 v/mil

1.1

Volume Resistivity 8 x 10<sup>14</sup> ohm-cm

## **Engineering Excellence**

For technical information and support call 1-800-552-0299 or visit our website at

