



Toll Free: 87 PERMATEX
(877-376-2839)

10 Columbus Blvd., Hartford,
Connecticut 06106

6875 Parkland Boulevard, Solon
Ohio 44139

Technical Data Sheet

SEAL+LOCK Thread Compound

INDUSTRIAL

PRODUCT DESCRIPTION

Permatex® SEAL+LOCK Thread Compound is a unique anaerobic formulation that combines thread sealing properties with the strength and locking capability of Permatex® Blue Threadlocker. This sealant is a smooth, white paste-like compound that is formulated for fast, responsive curing in the absence of air between close fitting metal threads and fixtures. Permatex® SEAL+LOCK Thread Compound allows you to create a water and air tight seal with reassurance that the assembly is locked in place and will not loosen.

NOTE: Not compatible with plastics and rubbers.

PRODUCT BENEFITS

- Creates air and water tight seal
- Cures without cracking or shrinkage
- Prevents galling and corrosion
- Controlled strength; removable with hand tools
- Temperature and solvent resistant
- Immediate low pressure sealing
- Easy cleanup; no curing beyond fittings

TYPICAL APPLICATIONS

Recommended automotive uses:

- Freeze plugs
- Oil pressure sensor
- Fuel line supply nuts and bolts
- Fuel injector
- Coolant temperature sensor
- Power steering cooler lines
- Brake master cylinder line nuts
- A/C systems
- Plumbing systems

Recommended hardware uses:

- Metal plumbing connections
- Garden hose and sprinkler connections
- Pipe plugs

DIRECTIONS FOR USE

For assembly

1. For best performance, clean all threads with a cleaning solvent such as Permatex® Brake and Parts Cleaner and allow to dry.
2. Determine if the threads to be bonded are **Active** or **Inactive Metals** (Ref: Cure Speed vs. Substrate on the second page). If material is an **Inactive Metal**, spray all threads with Permatex® Surface Prep and allow 30 seconds to dry. Priming is not required if the material is

an **Active Metal**. If unknown, it is always best to use the activator.

3. Knead tube of Thread Compound before use.
4. Apply sealant to leading threads of the male fitting, leaving the first thread free of sealant. Apply to only 3/4 of a thread turn; it is not necessary to apply to all threads.
5. Assemble parts and tighten to recommended torque.
6. Allow to cure 72 hours for full strength. To accelerate cure time, prep threads with Permatex® Surface Prep Activator.

For Cleanup

1. Residual liquid films and/or fillets outside the joint are readily soluble in Permatex® Brake and Parts Cleaner.
2. Cured product can be removed with a combination of soaking in Permatex® Gasket Remover and mechanical abrasion such as a wire brush.

For Disassembly

1. Remove with standard hand tools.
2. In the rare instance where hand tools do not work, because of excessive engagement length, apply localized heat to metal thread until approximately 232°C (450°F). Disassemble while hot.

For Reassembly

1. Remove loose product from all surfaces.
2. Apply primer to all threads, regardless of metal type.
3. Assemble and tighten as usual.

PHYSICAL PROPERTIES OF UNCURED MATERIAL

	Typical Value
Chemical Type	Methacrylate ester
Appearance	White opaque paste
Odor	Acrid
Specific Gravity	1.10
Viscosity @ 25°C, cP	250,000-
Brookfield RVF, spindle #7, @ 2 RPM	600,000
Flash Point (T.C.C.) °F	>200
Chemical resistance	Gasoline, oil, water, glycol, hydraulic fluid

TYPICAL CURING PERFORMANCE

Cure speed vs. temperature

The rate of cure will depend on the ambient temperature. **Full cure** is attainable in 72 hours at room temperature, 22°C (72°F), or 3 hours at 93°C (200°F).

NOT FOR PRODUCT SPECIFICATIONS.

THE TECHNICAL DATA CONTAINED HEREIN ARE INTENDED AS REFERENCE ONLY.

PLEASE CONTACT PERMATEX, INC., TECHNICAL SERVICE DEPARTMENT FOR ASSISTANCE AND RECOMMENDATIONS FOR YOUR SPECIFIC APPLICATION.
PERMATEX, INC., HARTFORD SQUARE NORTH, 10 COLUMBUS BOULEVARD, HARTFORD, CT 06106 PHONE - (1-877)PERMATEX Revised 03/10

Cure speed vs. substrate

The rate of cure will depend upon the type of material used. Permatex® SEAL+LOCK Thread Compound will react faster and stronger with **Active Metals**. However, **Inactive Metals** will require the use of Permatex® Surface Prep Activator to obtain maximum strength and cure speed at room temperature.

Active Metals	Inactive Metals
Soft Steel Iron	Bright Platings
Copper	Anodized Surfaces
Brass	Titanium
Manganese	Zinc
Bronze	Pure Aluminum
Nickel	Stainless Steel
Aluminum Alloy	Cadmium

warranties of merchantability or fitness for a particular purpose, arising from sale or use of Permatex, Inc. products and disclaims any liability for consequential or incidental damages of any kind, including lost profits. This product may be covered by one or more United States or foreign patents or patent applications

Cure speed vs. activator

Where cure speed is unacceptably long, or large gaps are present, applying Permatex® Surface Prep Activator to the surface will improve cure speed. Assemblies will typically fully cure in 24 hours with activator.

PHYSICAL PROPERTIES OF CURED MATERIAL

(After 72 hr at 72°F on 3/8-16 steel Grade 8 Nuts and Grade 5 bolts)

	Typical Value
Breakaway Strength	50-100 in-lbf
Shear Strength	>1000 PSI
Temperature Range	-60°F to 300°F (-51°C to 150°C)

Chemical Resistance

Aged under listed conditions and tested at 22°C(72°F)

Chemical	Temp	Time	Initial Strength Retained
Engine Oil	150°C	500 hr	160%
ATF	150°C	500 hr	160%
50:50 Water/Glycol	120°C	500 hr	70%
Gasoline	25°C	500 hr	155%

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

ORDERING INFORMATION

Part Number	Container Size
57535	35 mL tube, carded

STORAGE

Products shall be ideally stored in a cool, dry location in unopened containers at a temperature between 14°F (-10°C) to 86°F (30°C). Optimal storage is at the lower half of this temperature range. To prevent contamination of unused product, do not return any material to its original container.

NOTE

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. **Permatex, Inc. specifically disclaims all warranties expressed or implied, including**

