

## Stone Seam

### Stone Seam Pro 1000

#### Bulk Adhesive Seaming Solutions Flowing Adhesives

##### Stone Seam Pro SS1000 Acrylic Flowable Clear Seaming Resin

#### 1. DESCRIPTION

Stone Seam PRO SS1000 is a two-part methacrylate, clear acrylic flowable seaming adhesive designed for the Inconspicuous bonding of various substrates, including hard surface products including granite, engineered stone, quartz, marble, cultured marble, glass, sintered stone, porcelain, and various ceramic surfaces). Combined at a ratio of 100 to 5, Stone Seam PRO SS1000 has a working time of 4 to 6 minutes and achieves nearly 90 percent of its ultimate strength in 12 to 15 minutes at room temperature curing. Stone Seam PRO SS1000 provides high strength bonds to the above reference surfaces with generally no preparation effort. Stone Seam PRO SS1000 adhesives are UV STABLE, AND WILL NOT YELLOW OVER TIME.

**Company Identification: Chemical Concepts, Inc.**

410 Pike Road Huntingdon Valley, PA 19006 United States

Customer Service: 800.220.1966

chemical-concepts.com

sales@chemical-concepts.com

#### 2. CHARACTERISTICS:

##### Room Temperature Cure

- Working Time
- Fixture Time
- Can be Moved In
- Operating Temp.
- Gap Filling
- Mixed Density
- Flash Point

##### Properties

4 to 6 minutes (at 75°F/ 24°C)  
12 to 15 minutes (at 75°F/ 24°C)  
20 minutes  
65°F to 85°F (18°C to 30°C)  
.125 inches  
8.1 lbs./gal (.96 g/cc)  
51°F (11°C) – See SDS for more safety information

#### 3. CHEMICAL RESISTANCE:

##### Excellent Resistance to:

- Hydrocarbons
- Acids and Bases
- Vinegar
- Wine and Condiments
- Most Household Foods

##### Susceptible to:

Polar Solvents  
Super Strong Acids and Bases

#### 4. PHYSICAL PROPERTIES:

##### Uncured:

- Viscosity(cps)
- Color
- Density (lbs./gal)
- Mix Ratio (wt. or vol)

##### Resin

2,000 – 3,000  
Crystal Clear  
8.2  
100

##### Activator

15,000 to 20,000  
Milky Clear  
8.0  
5

**Stone Seam**  
**Stone Seam Pro 1000**

**5. MECHANICAL PROPERTIES:**

Tensile Strength (ASTM D638)	Substrate	Results	Failure Type
• Strength, psi	Quartz	2,500+	Substrate
• Strength, psi	Porcelain	2,500+	Substrate
• Strength, psi	Natural Stone	1,000+	Substrate

**6. HANDLING AND APPLICATION:**

**Stone Seam PRO** resin (Part A) and activator (Part B) are flammable. Contents include Methacrylate ester and acids. Keep containers closed after use. Wear gloves and safety glasses to avoid skin and eye contact. Wash with soap and water after skin contact. In case of eye contact, flush with water for 15 minutes and get medical attention. Harmful if swallowed. Keep out of the reach of children. Keep away from heat, sparks, and open flames. Do not smoke cigarettes or anything else while handling or near the product. Refer to the Stone Seam PRO Safety Data Sheet for more complete safety instruction. To assure maximum bond strength, surfaces must be mated together within the specified working time, and all clamps affixed within that time. Use sufficient material to ensure that the joint is completely filled when parts are mated and clamped. Avoid over clamping parts, which may cause a dry joint or a joint starved of adhesive. All adhesive application, part positioning, fixturing, and clamping should occur before the working time of the adhesive has expired. After the indicated working time, parts must remain undisturbed until the fixture time is completed. Components bonded, adhesive, and shop temperature can have a significant effect on the work and fixture time of the adhesive. Application of Stone Seam PRO adhesive at temperatures between 65°F and 85°F (18°C and 30°C) will ensure proper cure. Temperatures below 65°F (18°C) will slow cure and fixture speed. Stone Seam PRO adhesives will still react, but will take longer. Temperatures above 85°F (18°C and 30°C) will increase cure and fixture speeds, and there's a risk that the adhesive will be hardened or too thick to bond materials. The viscosity of Stone Seam PRO adhesives is affected by temperature.

**NOTE:** Because of the curing features of Stone Seam PRO adhesives, large amounts of heat are generated when large masses of material are mixed at one time. The heat generated by the exotherm resulting from mixing large amounts of adhesive can result in a boiling of the monomer in the adhesive (methyl methacrylate), resulting in the release of trapped air, steam and volatile gasses. To prevent this, use only enough material as needed for use within the working time for the product, and confine the gap or spread out the material to no more than .5 inches.

**7. HANDLING AND STORAGE**

The shelf life of Stone Seam PRO is twelve (12) months from the date of manufacture based upon continuous storage at room temperature (77°F or 25°C). Storage of Stone Seam PRO adhesives in refrigerated compartments will extend the shelf life even more. Do not store Stone Seam PRO adhesive or any other adhesives in a refrigerator which has food or lunch products in them. Be sure to bring Stone Seam PRO adhesives to room temperature for 24 hours before use, otherwise longer cure and fixture times may be expected. Long-term storage at temperatures above room temperature will shorten the shelf life of Stone Seam PRO adhesives considerably. Storage at temperatures above 100°F or 38°C could shorten the shelf life to less than one month. Stone Seam PRO adhesives contain no water, so freezing of the adhesive for short periods is permissible, but is not encouraged.

**8. ADDITIONAL INFORMATION**

**NOTE:** Information contained herein is based on tests we believe to be reliable and accurate. It is offered in good faith for the benefit of the consumer. The Company shall not be liable for any injury, loss, or damage in the use or handling of its chemical products since conditions and use are beyond our control. In every case, we urge and recommend the user conduct tests to determine to their own satisfaction that the product is of acceptable quality and suitability for their particular purpose under their own operating conditions. Statements concerning possible use of our products are not intended as recommendations to use our products in the infringement of any patent, or for any particular purpose or application. These products are intended for industrial use only.