



**TECHNICAL DATA SHEET**  
**TDS #: RP 2000**  
**CYANOACRYLATE ADHESIVE**  
REVISED: DECEMBER/2010

**ADVANCE PERFORMANCE SERIES**  
**RP 2000 CYANOACRYLATE ADHESIVE**  
GENERAL PURPOSE BONDING

**DESCRIPTION:**

RP 2000 is a high viscosity, rapid curing, cyanoacrylate adhesive. It is designed to bond a wide range of similar and dissimilar materials with good gap filling properties. Handling strength in most applications is in 15 seconds.

**PHYSICAL PROPERTIES:**

Color: Clear  
Viscosity: 2000 cps  
Specific Gravity: 1.09  
Base: Ethyl

**PERFORMANCE PROPERTIES:**

Substrate	Fixture Time	Bond Strength
Steel	< 25 Seconds	> 2100 psi
Aluminum	< 20 Seconds	> 1750 psi
Neoprene	< 10 Seconds	> 750 psi
ABS	< 15 Seconds	> 900 psi
PVC	< 10 Seconds	> 900 psi
Polycarbonate	< 30 Seconds	> 900 psi
Phenolic	< 10 Seconds	> 850 psi

NOTE: Method used, ISO 4587.

**Tensile Strength:**

Steel: > 1800 psi

NOTE: Method used, ISO 6922

**ELECTRICAL PROPERTIES:**

Dielectric Constant ASTM D 150 Dissipation Factor  
1 kHz 2 to 3.50/ < 0.02

Volume Resistivity ASTM D 257:  $2 \times 10^{15}$  to  $10 \times 10^{15}$

**FACTORS AFFECTING CURE SPEED:**

**GAP:** Thin bond line results in faster cure speed. Larger gaps will lengthen cure speed.

**HUMIDITY:** Cure and fixture times can be influenced by the humidity conditions at the time of assembly. The higher the RH the faster cure and fixture times will be. Fixture time data based on our testing is conducted at 50% relative humidity.

**NON WARRANTY:** Information contained herein is based on test and information we believe to be reliable and accurate. It is offered in good faith for the benefit of the consumer. ASI shall not be liable for any injury, loss, or damage, in the use of its chemical products since the conditions of use are beyond our control. In every case we urge and recommend the user conduct tests to determine to their own satisfaction that the product is of acceptable quality and suitable for their particular purpose under their own operating conditions. Statements concerning the possible use of our products are not intended as recommendations or to use our products in the infringement of any patent. These products are for Industrial Use only.

**What we bond:**

<b>ABS</b>	<b>NBR</b>
<b>Acrylic</b>	<b>Neoprene</b>
<b>Aluminum</b>	<b>Nitrile</b>
<b>Bakelite</b>	<b>Nylon</b>
<b>Brass</b>	<b>Phenolic</b>
<b>Chloroprene</b>	<b>Polycarbonate</b>
<b>Chrome</b>	<b>Polyester</b>
<b>Cooper</b>	<b>Polystyrene</b>
<b>EPDM</b>	<b>Porcelain</b>
<b>Fiberglass</b>	<b>PVC</b>
<b>Latex</b>	<b>SBR</b>
<b>Leather</b>	<b>Steel</b>
<b>Natural Rubber</b>	<b>Valox</b>
	<b>Wood</b>

**CHEMICAL/SOLVENT RESISTANCE:**

% OF STRENGTH RETAINED AFTER AGING FOR 500 HOURS

<b>GASOLINE @ 22°C:</b>	<b>100%</b>
<b>ISOPROPANOL @ 22°C:</b>	<b>100%</b>
<b>ETHANOL @ 22°C:</b>	<b>100%</b>
<b>FREON TA @ 22°C:</b>	<b>100%</b>
<b>MOTOR OIL @ 40°C:</b>	<b>100%</b>
<b>POLYCARBONATE 40°C @ 95% RH</b>	<b>100%</b>

**DIRECTIONS FOR USE:**

For optimum results parts should be clean and free from any contamination on the bonding surface. If parts do not mate flush together use a higher viscosity product to compensate for the gap. Any excess adhesive can be removed using Remove Debonder.

**STORAGE:**

Store product in unopened containers, out of direct sunlight, in a dry location. Material should be stored at or below 22°C. For extended shelf life unopened containers of the product may be refrigerated.



chemical-concepts.com

**800.220.1966**

410 Pike Road • Huntingdon Valley, PA 19006