

Features & Benefits

- Adhesion to a wide variety of substrates
- Full cure at room temperature
- Easy to apply
- Good gap fill ability
- Excellent thermal conductivity
- Designed to meet the requirements of UL94

Description

PERMABOND® MT3836 two-part, modified hybrid silane polymer adhesive designed for sealing and bonding applications. It has excellent adhesion to polycarbonate, ABS, Nylon and other plastics as well as a variety of different metals.

The cured adhesive has been designed to meet the fire retardancy requirements of UL94 V-0.

Typical Physical Properties of Uncured Adhesive

	MT3836A	MT3836B
Chemical Composition	MS resin	Polyol/water
Colour	White	Yellow
Mixed Appearance	Creme	
Viscosity @ 25°C	350,000 mPa.s (cP)	300,000 mPa.s (cP)
Specific Gravity	1.5	1.2

Typical Curing Properties


Mix ratio	2:1 by volume
Maximum gap fill	5 mm (0.2")
Usable / pot life @23°C	5-30 mins
Handling time	2-3 hours
Full cure	>72 hours

Typical Performance of Cured Adhesive

Shear strength after 72 hours (ISO4587)	Stainless Steel: 2-2.5 N/mm ² (290 - 360psi) ABS: 1.5 N/mm ² (220psi) Nylon: 1 N/mm ² (145psi)
Tensile strength after 72 hours (ASTM D 2095)	2 N/mm ² (290psi)
Peel strength (ISO4578)	50-70 N/25mm (11-16 PIW)
Hardness (ISO 868) after 72 hours	60 Shore A
Elongation at break (DIN 53504) after 72 hours	>100%
Shrinkage after 72 hours	0.5%
Thermal conductivity	1.05 W/(m.K)
Coefficient of thermal expansion	110 x 10 ⁻⁶ mm/mm/°C
Dielectric strength	18-20 kV/mm

*Strength results will vary depending on the level of surface preparation and gap.

Strength Development




Graph shows typical strength development of bonded components at 23°C. Curing at higher or lower temperatures may affect cure speed.

The information given and the recommendations made herein are based on our research and are believed to be accurate but no guarantee of their accuracy is made. In every case we urge and recommend that purchasers before using any product in full-scale production make their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purpose under their own operating conditions. THE PRODUCTS DISCLOSED HEREIN ARE SOLD WITHOUT ANY WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED.

No representative of ours has any authority to waive or change the foregoing provisions but, subject to such provisions, our engineers are available to assist purchasers in adapting our products to their needs and to the circumstances prevailing in their business. Nothing contained herein shall be construed to imply the non-existence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of this patent. We also expect purchasers to use our products in accordance with the guiding principles of the Chemical Manufacturers Association's Responsible Care® program.

Hot Strength



"Hot strength" shear strength tests performed on mild steel. Fully cured specimens conditioned to pull temperature for 30 minutes before testing at temperature.

MT3836 can withstand higher temperatures for brief periods (such as for paint baking and wave soldering processes) providing the joint is not unduly stressed. The minimum temperature the cured adhesive can be exposed to is -40°C (-40°F) depending on the materials being bonded.

Additional Information

This product is not recommended for use in contact with strong oxidizing materials.

Information regarding the safe handling of this material may be obtained from the safety data sheet.

Users are reminded that all materials, whether innocuous or not, should be handled in accordance with the principles of good industrial hygiene.

This Technical Datasheet (TDS) offers guideline information and does not constitute a specification.

Surface Preparation

Surfaces should be clean, dry and grease-free before applying the adhesive. Use a suitable solvent (such as acetone or isopropanol) for the degreasing of surfaces. Some metals such as aluminium, copper and its alloys will benefit from light abrasion with emery cloth (or similar), to remove the oxide layer.

Directions for Use

1. Measure volumetrically 2 parts resin to 1 part hardener. Mix thoroughly taking care not to entrap air. Adhesive can be applied and mixed by automated dispensing equipment. If using cartridges, put cartridge in dispensing gun and affix static mixing nozzle.
2. Apply material to one of the substrates.
3. Join the parts. Parts must be joined within the usable pot life.
4. Large quantities and/or higher temperature will decrease the usable life or pot life.
5. Apply pressure to the assembly by clamping for 2-3 hours or until handling strength is obtained.
6. Full cure will be obtained after a **minimum of 72 hours** at 23°C (73°F).

NB. Exercise caution when mixing large quantities due to exothermic reaction.

Video Links

Surface preparation:

<https://youtu.be/8CMOMP7hXjU>



Two-part directions for use:

<https://youtu.be/GRX1RyknYqc>



Storage & Handling

Storage Temperature	5 to 25°C (41 to 77°F)
---------------------	------------------------



chemical-concepts.com

800.220.1966

410 Pike Road • Huntingdon Valley, PA 19006

www.permabond.com

• UK: 0800 975 9800

• General Enquiries: +44 (0)1962 711661

• US: 732-868-1372

• Asia: + 86 21 5773 4913

info.europe@permabond.com

info.americas@permabond.com

info.asia@permabond.com

The information given and the recommendations made herein are based on our research and are believed to be accurate but no guarantee of their accuracy is made. In every case we urge and recommend that purchasers before using any product in full-scale production make their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purpose under their own operating conditions. THE PRODUCTS DISCLOSED HEREIN ARE SOLD WITHOUT ANY WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED.

No representative of ours has any authority to waive or change the foregoing provisions but, subject to such provisions, our engineers are available to assist purchasers in adapting our products to their needs and to the circumstances prevailing in their business. Nothing contained herein shall be construed to imply the non-existence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of this patent. We also expect purchasers to use our products in accordance with the guiding principles of the Chemical Manufacturers Association's Responsible Care® program.

Permabond MT3836

Global TDS Revision 2

12 January 2022

Page 2/2

FOR PROFESSIONAL OR INDUSTRIAL USE ONLY. KEEP OUT OF REACH OF CHILDREN